

5.0%

Not yet Date: 2021-12-09 05:22 UTC

* All sources 91 | Internet sources 20 | Publisher sources 6 | Organization archive 4 | Plagiarism Prevention Pool 19

- ✓ [0] [14.139.13.47:8080/jspui/handle/10603/94280](#)
3.1% 24 matches

- ✓ [4] [www.chalcogen.ro/165_MunirT.pdf](#)
0.9% 10 matches

- ✓ [9] [from a PlagScan document dated 2018-06-25 09:55](#)
0.4% 11 matches

- ✓ [10] [from a PlagScan document dated 2019-03-05 01:22](#)
1.0% 7 matches

- ✓ [12] [www.pjps.pk/wp-content/uploads/pdfs/34/5/Paper-2.pdf](#)
0.3% 7 matches

- ✓ [15] [www.researchgate.net/publication/326827963_Electrical_conductivity_and_chemical_stability_of_pure_and_Zr_substituted_Ba](#)
0.0% 8 matches

- ✓ [31] [Structural, spectroscopic and optical properties of pure and gadolinium doped neodymium phosphate nanoparticles prepared](#)
0.0% 5 matches

- ✓ [32] [A comparative study of spin coated transparent conducting thin films of gallium and aluminum doped ZnO nanoparticles.\(Res](#)
0.0% 4 matches

- ✓ [34] [www.researchgate.net/publication/328851429_Review_of_electrical_properties_of_graphene_conductive_composites](#)
0.4% 2 matches

- ✓ [35] [from a PlagScan document dated 2021-08-05 07:58](#)
0.3% 3 matches

- ✓ [43] ["Fabrication and characterization of carbon coated aluminum oxide for separation of dyes and heavy metals from water.docx" d](#)
0.0% 3 matches

- ✓ [44] [from a PlagScan document dated 2016-06-30 08:21](#)
0.0% 4 matches

- ✓ [47] [from a PlagScan document dated 2019-07-25 12:32](#)
0.0% 2 matches

- ✓ [49] [sphinxsai.com/2015/ch_vol8_no6/1/\(297-302\)V8N6CT.pdf](#)
0.0% 3 matches

- ✓ [52] [www.researchgate.net/publication/257223470_Electrochemical_characterization_of_Li2MnO3-LiNi13Co13Mn13O2-LiNiO2_catho](#)
0.0% 2 matches

- ✓ [54] [from a PlagScan document dated 2018-11-21 14:22](#)
0.0% 3 matches

- ✓ [58] ["sensors-18-03237-v2.pdf" dated 2018-10-30](#)
0.0% 2 matches

- ✓ [59] [from a PlagScan document dated 2017-07-11 10:39](#)
0.0% 3 matches

- ✓ [60] [Structural and optical properties of Cu-doped ZnO nanorods by silar method](#)
0.0% 1 matches

- ✓ [61] [from a PlagScan document dated 2021-08-24 05:12](#)
0.0% 2 matches

























- ✓ [62] [from a PlagScan document dated 2020-03-28 18:39](#)
0.0% 1 matches

- ✓ [63] [from a PlagScan document dated 2019-03-05 09:18](#)
0.0% 1 matches

- ✓ [64] [from a PlagScan document dated 2018-01-11 21:48](#)
0.0% 2 matches

- ✓ [65] [link.springer.com/10.1007/s10854-021-05570-w](#)
0.0% 2 matches
1 documents with identical matches

- ✓ [67] [www.researchgate.net/publication/303867097_Effect_of_barium_doping_on_the_physical_properties_of_zinc_oxide_nanoparti](#)
0.0% 2 matches

- ✓ [71]  from a PlagScan document dated 2016-09-08 05:44
0.0% 2 matches
-
- ✓ [72]  www.researchgate.net/publication/232528333_Does_doping_with_aluminum_alter_the_effects_of_ZnO_nanoparticles_on_the
0.0% 2 matches
-
- ✓ [73]  pubmed.ncbi.nlm.nih.gov/24811353/
0.0% 1 matches
-
- ✓ [74]  link.springer.com/chapter/10.1007/978-3-319-16006-1_15
0.0% 2 matches
⊕ 1 documents with identical matches
-
- ✓ [76]  from a PlagScan document dated 2020-11-16 05:55
0.0% 1 matches
-
- ✓ [77]  researchgate.net/figure/Scheme-1-Representation-of-functional-groups-attached-to-the-surface-of-CNCs-CNCa-and_fig1_25754
0.0% 1 matches
-
- ✓ [78]  from a PlagScan document dated 2020-05-22 00:00
0.0% 1 matches
-
- ✓ [79]  "Final Awais sensors-462270 for proof.pdf" dated 2019-03-15
0.0% 1 matches
⊕ 1 documents with identical matches
-
- ✓ [81]  Structure–property correlation of pure and Sn-doped ZnO nanocrystalline materials prepared by co-precipitation
0.0% 1 matches
⊕ 2 documents with identical matches
-
- ✓ [84]  "The subtle but substantial distinction between ammonium- and phosphonium-based DESs_MolLiq 2021.pdf" dated 2021-03-10
0.0% 1 matches
⊕ 1 documents with identical matches
-
- ✓ [86]  from a PlagScan document dated 2020-09-18 13:57
0.0% 1 matches
-
- ✓ [87]  from a PlagScan document dated 2020-08-18 07:29
0.0% 1 matches
⊕ 1 documents with identical matches
-
- ✓ [89]  from a PlagScan document dated 2019-08-06 12:40
0.0% 1 matches
-
- ✓ [90]  from a PlagScan document dated 2018-02-17 00:07
0.0% 1 matches
-
- ✓ [91]  from a PlagScan document dated 2017-08-17 10:55
0.0% 1 matches
-
- ✓ [92]  Preparation and characterization of Cd-doped ZnO thin films by spin coating method
0.0% 1 matches
-
- ✓ [93]  www.ias.ac.in/article/fulltext/pram/087/01/0004
0.0% 1 matches
-
- ✓ [94]  Co-assembled ZnO (shell) – CuO (core) nano-oxide materials for microbial protection
0.0% 1 matches
-
- ✓ [95]  www.researchgate.net/figure/Validation-of-numerical-model-with-previous-published-data-for-various-fluids-based-ORC_tbl1_2
0.0% 1 matches
-
- ✓ [96]  www.sciencedirect.com/topics/physics-and-astronomy/wurtzite
0.0% 1 matches
-
- ✓ [97]  pubmed.ncbi.nlm.nih.gov/31921648/
0.0% 1 matches
-
- ✓ [98]  www.researchgate.net/figure/The-wurtzite-crystal-structure-The-large-white-spheres-are-the-cations-the-small-black_fig1_2389
0.0% 1 matches
-
- ✓ [99]  www.degruyter.com/document/doi/10.1515/zna-2019-0157/html
0.0% 1 matches
-
- ✓ [100]  pubs.rsc.org/en/content/getauthorversionpdf/c9se01299k
0.0% 1 matches

PlagLevel: 5.0% selected / 14.9% overall

62 matches from 101 sources, of which 32 are online sources.

Settings

Data policy: *Compare with web sources, Check against organization repository, Check against the Plagiarism Prevention Pool*

Sensitivity: *High*

Bibliography: *Bibliography excluded*

Citation detection: *Highlighting only*

Whitelist: --

Analyses of structural and electrical properties of aluminium doped ZnO-NPs by experimental and mathematical approaches

Arslan Mahmood¹, Tariq Munir*¹, M. Fakhar-e-Alam¹, Muhammad Atif², Kaleem Shahzad¹,
K.S. Alimgeer³, Tuan Nguyen Gia^{4*}, Hijaz Ahmed^{5,6}, Shafiq Ahmad⁷

¹Department of Physics, Government College University Faisalabad (GCUF), Allama Iqbal Road, Faisalabad 38000, Pakistan

²Department of Physics and Astronomy, College of Science, King Saud University, Riyadh, 11451, Saudi Arabia

³Department of Electrical and Computer Engineering, COMSATS University, Islamabad, Islamabad campus, Pakistan

⁴Department of Computing, University of Turku, 20500, Turku, Finland

⁵Department of Basic Sciences, University of Engineering and Technology, Peshawar 25000, Pakistan

⁶Section of Mathematics, International Telematic University Uninettuno, Corso Vittorio Emanuele II, 39, 00186 Roma, Italy

⁷Industrial Engineering Department, College of Engineering, King Saud University, P.O. Box 800, Riyadh 11421, Saudi Arabia

*Corresponding Authors: Department of Computing, University of Turku, 20500, Turku, Finland (Tuan Nguyen Gia)
E-mail: tuan.nguyengia@hotmail.com, tariqmunir@gcuf.edu.pk

Abstract

Pure and aluminium doped ZnO-NPs were played the central role in every field of life due to extraordinary physical, chemical and electrical properties.^[34] The main objective of the present research was used to enhance the electrical conductivity and reduce the electrical resistivity of aluminium doped zinc oxide-NPs. Synthesis of pure and aluminium doped zinc oxide-NPs ($Zn_{1-x}Al_xO$) at $x=0, 2.5, 5, 7.5$ and 10 wt % was carried out by co-precipitation method.^[0] The XRD results depicted that hexagonal wurtzite crystal structure and crystallite size in the range of 13 - 25 nm were calculated by using Debye-Scherrer's equation. Likewise, the non-uniform, irregular and

pore like surface morphology of the prepared NPs was evident from SEM micrographs.^[10] Various functional groups (CH, CO, OH and ZnO) attached to the surface of aluminium doped zinc oxide-NPs was identified by FTIR analysis. The UV-VIS spectra also depicted a shift towards the blue region of the visible spectrum. In terms of electrical properties with the help of experimental and mathematical analyses of aluminum doped zinc oxide-NPs exhibited higher conductivity (1.34×10^{-6} to 1.43×10^{-3} S/cm) and lower resistivity (5.46×10^5 to $6.99 \times 10^2 \Omega\text{-cm}$).^[10] The present results suggest that the aluminum doped zinc oxide-NPs have been improved the structural and electrical properties which make it a good candidate for optoelectronic devices.

Keywords: Co-precipitation, Al-doped ZnO, Hexagonal wurtzite, Conductivity, Resistivity.




Figure 1: Graphical expression of pure and Al- doped ZnO-NPs

1. Introduction

Previous studies provided the information about the oxide base nanomaterials are used in textile, electronic, optoelectronic, sensing and biomedical fields due to multiple physical, chemical and biological properties (Munir et al., 2021). Nanoparticles can be manufactured such as natural resource as well as chemically and they are important materials in fuel cells, solar cells, bactericidal agents, batteries, sensors, photocatalytic and self-cleaning coatings (Al-Kahlout, 2012; Munir et al., 2020; Abutalib et al., 2020). The nanomaterials have been extensively used as multifunctional material owing to its non-toxicity, low cost, wide source, acid-base resistance and high catalytic activity. Moreover, the previous study reported that the three different types of defect such as point, line and surface defect are most common in crystals of oxide nanoparticles. ^[10] The point defect linked with donor and acceptor defect, which have an effect on the electrical behavior of the nanomaterials (Ischenko et al., 2005). But ZnO-NPs represents three type donor defects V_o , Zn_o and Zn_i , and three type acceptor defects O_{zn} , O_i and V_{zn} . Due to large band gap in ZnO-NPs indicate the multiple defects in crystal. The pure ZnO-NPs show the high resistivity and low conductivity by using the different doping agents to decrease the resistivity and improved the conductivity up to significant values (Shi et al., 2011).

The ZnO semiconductor nanomaterial belongs to group II-IV of the periodic table and high concentration of electron in ZnO-NPs represents n-type characteristics. It was shown that with tunable band gap (~3.37 eV) and doping with E.N (higher electronegative elements such as Cu, F, Al and Co) could alter electrical behavior (Kang et al., 2019). Its larger band gap energy and maximum excitation binding energy (~60 meV) make it feasible for higher temperature applications (Vadivel et al., 2014). During this study, ZnO-NPs synthesized with low-cost material and simple chemical technique and its electrical properties comparable to ITO materials. The ITO material is highly expensive and it was used at commercial scale. It is important to mention here that the physical and chemical properties of ZnO-NPs can be modified by using different transition elements like Al, Cu, In, Sn, Ag and Co as doping materials (Shui et al., 2009). Furthermore, the ionic radii of Al (53 pm) are much smaller as compared to Zn (88 pm) which favour its addition as doping without producing stress (Griffen, 1981; Lee et al., 2003). Here, discuss the synthesis of Al-doped ZnO-NPs was achieved through controlled stoichiometry and homogeneity at the

molecular level via co-precipitation method.^{[0]▶} The prepared pure and Al-doped ZnO-NPs were characterized by using various characterization techniques such as XRD, SEM, FTIR, UV-VIS and two probe methods.^{[0]▶} Moreover, these multiple characterization techniques were used to investigate the structural as well as electrical properties. For first time compare the experimental and mathematical modelling analysis such as second order polynomial function was applied on data for electrical properties. Finally, experimental and mathematical analysis shows that electrical conductivity increased and electrical resistivity decrease.

2. Experimental details

2.1. Chemicals

The following are the precursor such as Zinc nitrate hexahydrate (reagent grade {RG}, 98%), Aluminum nitrate nonahydrate (RG, 98%) and Sodium Hydroxide (RG \geq 98%) used to prepare the pure and aluminium doped zinc oxide-NPs.

2.2.^{[0]▶} Synthesis of pure and Al-doped ZnO-NPs

The 200 mL de-ionized water was used to prepare the solution of zinc nitrate (0.4 M) and the solution was stirred on magnetic stirrer for 20 min at 70°C. This followed the addition of NaOH buffer solution to maintain the pH (11-12) of the solution. After that the white precipitate was obtained by washing with de-ionized water to remove impurities and then oven-dried (100 °C for 24 h) and afterwards, prepared ZnO-NPs powder was annealed at 200 °C for 3 hours inside a muffle furnace. Likewise, the prepared Al-doped ZnO-NPs (2.5 %) aluminium nitrate solution was prepared in (0.4 M) zinc nitrate and the solution was stirred for 30 min at 70 °C on stirrer. Finally, the same procedure was repeated three time by various concentration (5.0, 7.5 and 10 wt %). The figure (1) represents the graphical expression of pure and aluminium doped zinc oxide-NPs.

2.3. Mathematical Modeling

In case of mathematical modeling the second order polynomial function was applied on the data of conductivity to investigate the behavior of conductivity of pure and aluminium doped zinc oxide-NPs.

2.4.^{[0]▶} Characterization of Al-doped ZnO-NPs

The different characterization techniques was used to investigate the structural and electrical properties of aluminium doped zinc oxide-NPs, which include XRD model (X'Pert³ MRD) was

preferred to identified the structure and Debye-Scherrer's equation (1) was used to calculate the crystallite size.

$$D = [(0.9\lambda) / \beta \cos\theta] \dots \dots \dots (1)$$

To investigate the surface morphology by using SEM model (Emcrafts) micrographs.¹⁹ The multiple functional groups attached on the surface of spectrum were identified by FTIR model (FTS-14) and the optical behavior of the aluminium doped zinc oxide-NPs was observed by using UV-VIS model (Perkin Elmer Lambda 2). Finally, the electrical resistivity and electrical conductivity were calculated by using IV two probe methods.

3. Results and discussion

3.1. XRD analysis

The crystalline behavior of the aluminium doped zinc oxide-NPs were investigated by XRD analysis and the hexagonal wurtzite crystal structure was identified from (Figure 2) by XRD spectrum. The spectrum of pure and aluminium doped zinc oxide-NPs shows no extra peak appeared by increasing the Al-concentration. Because the Al-dopant concentration was affected the intensity level of the different peaks and it was not affected the structure of ZnO-NPs. The conformation about the Al ion properly substituted into ZnO-NPs because the smaller ionic radii of Al⁺³(53 pm) as compared to Zn⁺²(88 pm). The miller indices of different diffracted peaks (100), (101), (102) and (112) were calculated and it was compared with previous reported JCPDS standard data (Card No. 80-0074) (Gherab et al., 2017; Bhuiyan et al., 2017, Norouzzadeh et al., 2020). Finally, it was expressed that the crystallite size of aluminium doped ZnO-NPs decreased via increasing Al-concentration was expressed in Table-1.




Figure 2: XRD spectrum of aluminum doped zinc oxide-NPs

Table 1: Shows the crystallite size of aluminium doped zinc oxide-NPs

Al dopant- ZnO NPs with different concentration (wt %)	Peak (101) (nm)	Peak (112) (nm)	Average size (nm)
0	25.31	24.6	24.9
2.5	21.3	20.7	21
5.0	19.0	18.5	18.7
7.5	16.5	14.1	15.3
10.0	13.7	12.3	13

3.2. FTIR analysis

The FTIR spectrum of Al-doped ZnO-NPs indicated that at higher concentration of Al atoms spectrum peaks slightly fluctuated and absorption spectrum from wavenumber 400-4000 cm^{-1} was expressed in (Figure 3). After that the several bands below 1000 cm^{-1} indicated inter-atomic vibration modes and band at 3600 cm^{-1} represented O-H stretching mode. Furthermore, the mode at 2400 cm^{-1} represents C-H rotational mode and stretching mode C=O vibration band exist in between 1400-1600 cm^{-1} . Finally, the peaks at 470 and 670 cm^{-1} represent the ZnO stretching mode (Piticescu et al., 2006; Akdag et al., 2016; Baghdadi et al., 2020).




Figure 3: FTIR spectrum of pure and aluminium doped ZnO-NPs

3.3. SEM analysis

Pure ZnO-NPs micrograph depicted irregular small and large grain size; while Al-doping agent represents the same pattern but an increase in grain size was evident. The images were collected at the same range 1.0 μm as shown (Figure 4) also expressed the pore like surface morphology and it was compared with previous published data. (Kant et al., 2021).




Figure 4: SEM patterns (A) Pure zinc oxide-NPs (B) aluminium doped ZnO-NPs

3.4. Electrical analysis

The resistivity and conductivity study explained that increase in aluminium concentration ($x = 0.00, 2.5, 7.5$ and 10.00 wt %) in ZnO as dopant material (Figure 5) improved its conductivity (1.34×10^{-6} to 1.43×10^{-3} S/cm) while decreased resistivity (5.46×10^5 to $6.99 \times 10^2 \Omega\text{-cm}$). The variation in resistivity and conductivity shows that Al substitution of Zn ions to improve the electrical properties of aluminium doped ZnO-NPs (Ahmad et al., 2013). Aluminium-doped ZnO-NPs shows high conductivity and low resistivity properties comparable of an expensive material Indium tin oxide (ITO) (Bhugul et al., 2015), which shows potential applications in electrical and optical devices.




Figure 5: Resistivity and conductivity of aluminium doped ZnO-NPs

3.5. UV-VIS analysis

The UV-visible spectra explained the absorbance band of Al-doped ZnO-NPs in (Figure 6). The spectra at 0, 2.5, 5.0, 7.5 and 10 wt % aluminium concentrations indicated that as increased dopant (Al) caused wavelength decreased which caused a spectrum shift towards shorter wavelength (blue shift). Pure ZnO exhibited absorbance peak at 376 nm, while aluminium doped material peak shift toward short-wavelength less than 376 nm (Sanguanprang et al., 2020; Zhang et al., 2017; Dhamodharan et al., 2017).




Figure 6: UV-VIS of aluminium doped ZnO-NPs

3.6. Mathematical Modeling analysis

The data was used to create mathematical modelling of conductivity against the increasing concentration of dopant agent. The behavior of data is exponentially increasing which leads to the proposal of modelling with second order polynomial as shown in equation (2). The method of least square error is used to fit the data and to extract unknown coefficients used in generic second order polynomial. Figure 7 shows the proposed second order polynomial for mathematical model of the data of conductivity. The data itself is also shown to evaluate the goodness of fit for the proposed model.

$$\text{Conductivity} = P_1 \times \text{Dopping}^2 + P_2 \times \text{Dopping} + P_3 \quad (2)$$




Figure 7: Data of conductivity (S/cm) as a function of doping concentration (wt.%). The proposed mathematical model of 2nd order polynomial confirms the suitability of the proposed model along with the extracted unknown parameters.

^[4] 4. Conclusions

The aluminium doped ZnO-NPs were synthesized via **co-precipitation method** and hexagonal wurtzite crystal **structure and crystallite size** decreased by increasing Al concentrations in ZnO-NPs was identified **by using XRD analysis**. **After that the** non-uniform and irregular pore like structure were identified by SEM analysis and FTIR **was used to calculate the different rotational and vibrational modes attached on the spectrum of pure and aluminium doped ZnO-NPs**. The UV-VIS analysis was use to observed the absorption at 376 nm and wavelength decrease by increasing doping concentration. Above all, the aluminium doped ZnO-NPs had better conductivity with decreased resistivity as compared to ZnO-NPs and the analysis also investigated by applying

mathematical modelling of second order polynomial function. Finally, the prepared nanomaterials (aluminium doped zinc oxide-NPs) were used in optoelectronics applications.

Acknowledgements

Researchers Supporting Project number (RSP-2021/397), King Saud University, Riyadh, Saudi Arabia.

References

- Abutalib, M. M., & Rajeh, A. (2020). Structural, thermal, optical and conductivity studies of Co/ZnO nanoparticles doped CMC polymer for solid state battery applications. *Polymer Testing*, 91, 106803.
- Ahmad, M., Ahmed, E., Zhang, Y., Khalid, N. R., Xu, J., Ullah, M., & Hong, Z. (2013). Preparation of highly efficient Al-doped ZnO photocatalyst by combustion synthesis. *Current Applied Physics*, 13(4), 697-704.
- Akdağ, A., Budak, H. F., Yılmaz, M., Efe, A., Büyükaydın, M., Can, M., & Sönmez, E. (2016, April). Structural and morphological properties of Al doped ZnO nanoparticles. In *Journal of Physics: Conference Series* (Vol. 707, No. 1, p. 012020). IOP Publishing.
- Al-Kahlout, A. (2012). ZnO nanoparticles and porous coatings for dye-sensitized solar cell application: Photoelectrochemical characterization. *Thin Solid Films*, 520(6), 1814-1820.
- Bhugul, V. T., & Choudhari, G. N. (2015). Synthesis and Studies on Nanocomposites of polypyrrole-Al-doped zinc oxide Nanoparticles. *International Journal of Scientific and Research Publications*, 5.
- Bhuiyan, M. R. A., Alam, M. M., Momin, M. A., & Mamur, H. (2017). Characterization of Al doped ZnO nanostructures via an electrochemical route. *International Journal of Energy Applications and Technologies*, 4(1), 28-33.
- Baghdadi, N., Salah, N., Alshahrie, A., & Koumoto, K. (2020). Microwave Irradiation to Produce High Performance Thermoelectric Material Based on Al Doped ZnO Nanostructures. *Crystals*, 10(7), 610.

- Dhamodharan, P., Manoharan, C., Bououdina, M., Venkadachalpathy, R., & Ramalingam, S. (2017). Al-doped ZnO thin films grown onto ITO substrates as photoanode in dye sensitized solar cell. *Solar Energy*, 141, 127-144.
- Gherab, K., Al-Douri, Y., Voon, C. H., Hashim, U., Ameri, M., & Bouhemadou, A. (2017). Aluminium nanoparticles size effect on the optical and structural properties of ZnO nanostructures synthesized by spin-coating technique. *Results in physics*, 7, 1190-1197.
- Griffen, D. T. (1981). Synthetic Fe/Zn staurolites and the ionic radius of $IVZn^{2+}$. *American Mineralogist*, 66(9-10), 932-937.
- Ischenko, V., Polarz, S., Grote, D., Stavarache, V., Fink, K., & Driess, M. (2005). Zinc oxide nanoparticles with defects. *Advanced Functional Materials*, 15(12), 1945-1954.
- Kang, K. M., Wang, Y., Kim, M., Lee, H. S., & Park, H. H. (2019). The Structural, Electrical, and Optical Properties of ZnO Ultra-thin Films Dependent on Film Thickness. *Journal of the Microelectronics and Packaging Society*, 26(2), 15-21.
- Kant, R., Sharma, D., & Chanchal, V. (2021). Enhancement in dielectric and optical properties of Al doped ZnO/reduced graphene oxide nanocomposite. *Materials Technology*, 1-8.
- Lee, J. H., & Park, B. O. (2003). Transparent conducting ZnO: Al, In and Sn thin films deposited by the sol-gel method. *Thin solid films*, 426(1-2), 94-99.
- Munir, T., Latif, M., Mahmood, A., Malik, A., & Shafiq, F. (2020). Influence of IP-injected ZnO-nanoparticles in Catla catla fish: hematological and serological profile. *Naunyn-Schmiedeberg's Archives of Pharmacology*, 393(12), 2453-2461.
- Munir, T., Mahmood, A., Ahmad, N., Atif, M., Alimgeer, K. S., Fatehmulla, A., & Ahmad, H. (2021). Structural, electrical and optical properties of $Zn_{1-x}Cu_xO$ ($x= 0.00-0.09$) nanoparticles. *Journal of King Saud University-Science*, 33(2), 101330.
- Norouzzadeh, P., Mabhouti, K., Golzan, M. M., & Naderali, R. (2020). Investigation of structural, morphological and optical characteristics of Mn substituted Al-doped ZnO NPs: A Urbach energy and Kramers-Kronig study. *Optik*, 204, 164227.
- Piticescu, R. R., Piticescu, R. M., & Monty, C. J. (2006). Synthesis of Al-doped ZnO nanomaterials with controlled luminescence. *Journal of the European Ceramic Society*, 26(14), 2979-2983.

- Sanguanprang, S., Phuruangrat, A., Thongtem, T., & Thongtem, S. (2020). Preparation of Visible-Light-Driven Al-Doped ZnO Nanoparticles Used for Photodegradation of Methylene Blue. *Journal of Electronic Materials*, 49(3), 1841-1848.
- Shi, H. Y., Deng, B., Zhong, S. L., Wang, L., & Xu, A. W. (2011). Synthesis of zinc oxide nanoparticles with strong, tunable and stable visible light emission by solid-state transformation of Zn (II)-organic coordination polymers. *Journal of Materials Chemistry*, 21(33), 12309-12315.
- Shui, A., Wang, S., Wang, H., & Cheng, X. (2009). Preparation and properties for aluminum-doped zinc oxide powders with the coprecipitation method. *Journal of the Ceramic Society of Japan*, 117(1365), 703-705.
- Vadivel, M., Babu, R. R., & Ramamurthi, K. (2014). Studies on the structural, optical and magnetic properties of Al doped ZnO nanoparticles. *International Journal of Chem Tech Research*, 7(3), 1206-1211.
- Zhang, X., Chen, Y., Zhang, S., & Qiu, C. (2017). High photocatalytic performance of high concentration Al-doped ZnO nanoparticles. *Separation and Purification Technology*, 172, 236-241.